

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
21 December 2000 (21.12.2000)

PCT

(10) International Publication Number
WO 00/76722 A2

- (51) International Patent Classification: B24B 31/00 (74) Agent: BARNARD, Eric, Edward; Brookes & Martin, High Holborn House, 52/54 High Holborn, London WC1V 6SE (GB).
- (21) International Application Number: PCT/GB00/02266
- (22) International Filing Date: 12 June 2000 (12.06.2000) (81) Designated States (national): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 9913658.2 11 June 1999 (11.06.1999) GB
- (71) Applicant (for all designated States except US): NSK-RHP EUROPEAN TECHNOLOGY CO. LIMITED [GB/GB]; Mere Way, Ruddington Fields Business Park, Ruddington, Nottinghamshire NG11 6JZ (GB).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): DODD, Andrew [GB/GB]; 6 Halls Brook, East Leake, Loughborough, Leicestershire LE12 6HE (GB). DICKS, Mark, Philip [GB/GB]; 20 Hine Avenue, Newark, Nottinghamshire NG24 2LH (GB). TAYLOR, Mark, Stephen [GB/GB]; 10 Batesman Road, East Leake, Loughborough, Leicestershire LE12 6LN (GB).
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— Without international search report and to be republished upon receipt of that report.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: IMPROVEMENTS IN ROLLING ELEMENTS BEARINGS

(57) Abstract: A method of treatment of a rolling element bearing component by hard particle abrasion to improve the surface topography of the component. The hard particle abrasion includes the steps of immersing the bearing component in a receptacle containing hard particles, preferably alumina, and agitating the component and/or hard particles to produce relative movement. Preferably the method is performed for between 10 minutes and 1 hour. The relative movement may be produced by rotating the component in one direction while the receptacle is rotated in the opposite direction. The surface finish of the component is preferably improved from around 0.13 μm to around 0.07 μm . Compressive stress in the surface of the component may also be improved, typically by between 200 MPa and 500 MPa. Rolling contact fatigue life of the component is also improved.

WO 00/76722 A2

TO 240 2592960